Frenos Sauleda s.a.
science friction

Barri del migdia S/N - E 08396
Sant Cebrià de Vallalta (Barcelona - Spain)
sauleda@frenossauleda.com
Tel. (+34) 93 763 11 20 Fax (+34) 93 763 10 61

ID Material	16
Responsable	R. Antich
Revision	6
Revision date	31/07/2021

SA80/M

SA80/M is grey molded friction material with a medium high friction coefficient reinforced with metal components. This material is recommended for machining, having excellent friction characteristics. The material consists phenolic resins with NBR bonding system, short fibres, friction modifiers, metal particles and fillers. SA80/M is fully cured and suitable for bonding and riveting.

Material data

Friction properties

Static Friction Coefficient (@15bar, from the box)	0.55±0.05 μ
Static Friction Coefficient (@15bar, 100ºC)	0.60±0.05 μ
Dynamic Friction Coefficient (10bar, 10m/s)	0.50±0.05
Wear Rate (@10bar, 15m/s)	60 (at 150 ºC)
Tº Fading (@10bar, 10m/s)	>340 °C

Physical properties

Hardness (DIN53505)	78±5 Shore-D
Specific Gravity (ASTM D792)	1.80±0.05 gr/cm3
Ignition Loss (ASTM D7348)	43±2 %

Mechanical properties

Tensile Strength (ASTM D638)	10±2 N/mm²
Compressive Strength (ISO 844:2014)	100±5 N/mm²
Shear Modulus (ASTM D2344-00)	1060±100 N/mm²
Poison coefficient (ASTM D638)	0.18±0.03
Young Modulus (ASTM D638)	2500±100 N/mm²

Recommended Working Values

Tº Max. Continuous Operation	250 °C
Tº Max. Intermittent Operation	350 °C

Material type

Rigid

Appearance / Formats



Applications

Callipers for industrial applications · Friction washers · Miscellaneous industrial brakes / clutches · Torque limitator

Price Level

€ € €


Reach (EC)1907/2023 - RoHS 2015/863/EU


Compliance


Others


Recommended Mating Surface	Perlitic cast iron, hardness HB150-200
Recommended Adhesives	Thermosetting adhesive
Oil Resistant	Yes

Charts









Rubbing speed, temperature and pressure are related. Changing any values will change other. The values shown represent typical conditions, but are not ultimate limits of the material.