Frenos Sauleda s.a.
science friction

Barri del migdia S/N - E 08396
Sant Cebrià de Vallalta (Barcelona - Spain)
sauleda@frenossauleda.com
Tel. (+34) 93 763 11 20 Fax (+34) 93 763 10 61

ID Material	23
Responsable	R. Antich
Revision	6
Revision date	31/07/2021

SAFF

SAFF is green rigid molded friction material, which offers a very high friction coefficient. This material is reinforced with glass fibers and has a good mechanical resistance. The material consists phenolic resins with a NBR bonding system, short and large fibres, friction modifiers and fillers. SAFF is fully cured and suitable for bonding and riveting.

Material data

Friction properties

Static Friction Coefficient (@15bar, from the box)	0.55±0.05 μ
Static Friction Coefficient (@15bar, 100ºC)	0.55±0.05 μ
Dynamic Friction Coefficient (10bar, 10m/s)	0.60±0.05
Wear Rate (@10bar, 15m/s)	25 (at 150 ºC)
Tº Fading (@10bar, 10m/s)	>350 °C

Physical properties

Hardness (DIN53505)	88±5 Shore-D
Specific Gravity (ASTM D792)	1.8±0.05 gr/cm3
Ignition Loss (ASTM D7348)	40±2 %
Acetone Extraction (ASTM D494)	0.15±0.02 %

Mechanical properties

Tensile Strength (ASTM D638)	15±5 N/mm²
Compressive Strength (ISO 844:2014)	175±5 N/mm²

Recommended Working Values

Tº Max. Continuous Operation	300 °C
Tº Max. Intermittent Operation	400 °C

Material type

Rigid

Appearance / Formats



Applications

Industral clutches · Rings segments for machinery · Torque limitator

Price Level

€ € €


Reach (EC)1907/2023 - RoHS 2015/863/EU


Compliance


Others


Recommended Mating Surface	Perlitic cast iron, hardness HB150-200
Recommended Adhesives	Thermosetting adhesive
Oil Resistant	Yes

Charts









Rubbing speed, temperature and pressure are related. Changing any values will change other. The values shown represent typical conditions, but are not ultimate limits of the material.